

Printing Quality

Darkness



Sharpness



0° barcode



90° barcode




Min. printable character



Graphics




Substrate Compatibility



Sensitivity

Printing speed






Resistance Test

Physical resistance

Slight exposure begins after approx. X cycles with a $680\mbox{G}$ weight load.



Water resistance test

The printed label was soaked in water at 100°C for 2 hours and then check whether the imprint of the label was significantly faded.



No significantly faded

Low-temperature test

The printed label was placed in a closed cold box at -17°C for 20 hours and then check whether the imprint of the label was significantly fallen off.



No significantly fallen off

Recommended Applications



Receipt and delivery labels for warehouses



Logistics



Pharmaceuticals



Daily chemicals



Pre-packaging



Refrigeration Industry



Hot working



Retail labels



Digital & electronics labels



Clothing tags



Labels for automobile industry



Chemical industry



and flowers

Nursery gardens



Production lines



Wooden products



Steel & iron manufacturing



Fixed assets



Flectrical equipment



Mechanical equipment




Luggage

Properties

PET film	Ribbon
Thickness: 4.5μm	Thickness: 8.1±0.3μm
Ink	
Color: black Melting point: 70±3°C	
Storage condition	
Temperature: 5~35°C Humidity: 20~80% Validity period: 12 months	

Product Comparison



Certifications and Permits



ROHS2.0



REACH



ISO9001/14001



MSDS



HALOGEN

Economical Enhanced Wax Ribbon

BARCODING THE WORLD



Hangzhou Todaytec Digital Co., Ltd.

All product specifications can be found at our website www.todaytec.com/en/



(Marketing Department: +86 571-8577-1623



marketing@todaytec.com.cn

